

[Original document](#)

DOUBLE MOLTEN HIGH MANGANESE STAINLESS STEEL

Publication number: JP1225754

Publication date: 1989-09-08

Inventor: JIEMUSU EI DANIERUZU; JIYOZEFU EI
DOUZETSUTO; JIYON JII TATSUKU

Applicant: ARMCO ADVANCED MATERIALS

Classification:







- international: **C22C38/00; C22C38/58; C22C38/00; C22C38/58;** (IPC1-
7): C22C38/00; C22C38/58

- European:

Application number: JP19890015214 19890126

Priority number(s): US19880152178 19880204

Also published as:

 EP0327053 (A1) US4828630 (A1) AR247249 (A1) EP0327053 (B1) ES2032224T (T) CA1324729 (C)[less <<](#)[View INPADOC patent family](#)[View list of citing documents](#)[Report a data error here](#)

Abstract not available for JP1225754

Abstract of corresponding document: **EP0327053**

A duplex stainless steel which is economical and balanced to provide a good combination of properties in the as-cast condition and resists thermal transformation to martensite due to the high levels of manganese. This steel is particularly suited for thin-walled castings for automotive underbody components. It is 30% to 60% ferrite and balance austenite and, in weight percent, consists essentially of: C - up to 0.07, Cr - 17 to 21.5, Ni - greater than 1 to less than 4, Mn - greater than 4 to 8, N - 0.05 to 0.15, Si - less than 2, Mo - less than 2, Cu - less than 1.5 and balance essentially Fe. v

Data supplied from the *esp@cenet* database - Worldwide